



**EUROTILES SEAL & FLEX** is a single component flexible cementitious waterproofing mortar engineered to provide excellent protection and waterproofing to rendered concretes and masonry.

## ADVANTAGES

- Flexible and watertight
- Excellent adhesion
- Fiber reinforced mortar
- Non-toxic
- Pressure-and-counter-pressure resistant
- Can fill-up gaps up to 5mm
- Suitable for contact with potable water

## USES

- Bathrooms and kitchen
- Terraces, walls
- Under-tile sealant for swimming pools and damp premises
- Roof decks with concrete topping
- G.I. roofing / G.I. sheets / seal roofing holes

## TECHNICAL DATA

<b>Pot life (30°C)</b>	4 - 5 hours
<b>Foot traffic</b>	24 hours
<b>Ponding test for tanks</b>	24 - 48 hours
<b>Adhesion to concrete</b>	> 1.5mpa
<b>Chloride content</b>	<0.001%

<b>Coverage</b>	3 sqm/4kg pail @ 2 coats
<b>Packaging</b>	4kg pail
<b>Storage</b>	cool, dry place
<b>Shelf life</b>	12 months (unopened container)

## HOW TO USE

### A. Substrate Preparation

- The substrate must be clean and sound, free from dust and without traces of oil or grease. All loose part must be raked out.
- Fill honeycombs and bubbles.
- During application, substrate must be partially damp but not running with water.

### B. Product Preparation

Prepare the compound using a stirrer machine or heavy-duty mixer at low speed (i.e. 300-500rpm). Follow below instructions to obtain an evenly mixed paste:

- Pour 320ml of clean water for every kilo of Eurotiles Seal and Flex into a suitable plastic pail/container.
- Gradually mix for 3 minutes until a plastic consistency is achieved.
- Let it stand for several minutes to eliminate bubbles in the mixture.

## C. Application

---

- Eurotiles Seal and Flex is applied by hand using brush or steel trowel.
- Apply the first coat with a quantity of 0.75kg to 1kg/m<sup>2</sup>
- After 1 to 2 hours (depending on the temperature), apply the second coat with a quantity of 0.75-1kg/m<sup>2</sup>.
- Coats can be floated using a filler knife or stainless steel float.
- For sealing G.I. roofing holes, use of fiber mesh is advised then apply topping after curing or once dried.

## PRECAUTIONS

- Temperature range: 5°C to 35°C.
- Apply minimum of two coats and take all necessary precautions to prevent over-fast drying
- Where possible, carry out exterior application in shady cool condition.
- Do not dampen between binders, cement, sand, admixtures and/or water.
- Do not use acid-based cleaning products.
- Always wear gloves when using the product.
- Install concrete topping or tiling immediately after curing to avoid exposure to UV.
- Do not immerse the product.

**DISCLAIMER:** Due to different working methods, the manufacturer is not liable for any damages and faulty outcomes arising from incorrect use of this product. Please follow the instructions mentioned above.

**PRODUCT MADE IN THE PHILIPPINES**

### EUROTILES INDUSTRIAL CORPORATION

Km 39 Emilio Aguinaldo Highway, Biga 2, Silang, Cavite  
Tel. No.: (632) 8635-2310 to 16 Fax No.: (632) 8635-2317

Web: [www.eurotilesconstructionchemicals.com](http://www.eurotilesconstructionchemicals.com) FB: @eurotilesconstchem IG: @eurotilesconstchem YT: Eurotiles Industrial Corporation